

**Tokai Extruded Graphite Data Sheet**

# ***EE/FE200***

Specific Gravity	g/cm <sup>3</sup>	1.65
Specific Resistance	μΩm	9.0
Young's Modulus	GPa	n/a
Flexural Strength	MPa	19.6
Tensile Strength	MPa	n/a
Shore Hardness	sHD	39
C.T.E	× 10 <sup>-6</sup> /°C	3.3
Thermal Conductivity	W/mK	144
Pore Size	μm	n/a
Porosity	%	17-20
Grain Size	mm	0.8
Gas Permeability	cm <sup>2</sup> /sec	n/a

All properties measured room temperatures except for C.T.E.  
 C.T.E. = Coefficient Thermal Expansion (R.T. to 1000°C)  
 Flexural Strength determined using third point loading

Note: All properties are typical values and are not to be used for specification limits

